an-vision

an-Viscoelastic

an-bfh 1.8% and 2.2%

Bio-Fermented Hyaluronate



- Excellent depth maintenance of the anterior chamber and the capsular bag
- Great protection of the endothelium
- No refrigeration necessary
- Effective protection against mechanical damages
- Easy to inject and to remove

Specification	an-bfh 1.8%	an-bfh 2.2%
Natrium hyaluronate	1.8%	2.2%
Molecular weight [mill. Daltons]	1.2 – 2.0	1.0 – 2.1
Viscosity* [mPas]	ca. 100,000	ca. 300,000
Osmolality [mOsm/kg]	270 - 400	270 - 400
Storage	2° - 25°C	2° - 25°C
pH	6.8 – 7.4	6.8 – 7.4
Contents [ml]	2.0	2.0
Shelf life [months]	42	42

*after steam sterilization

an-vision

an-Viscose

2% Hydroxypropylmethylcellulose (HPMC)



- **Provides excellent protection of the endothelial cells**
- **Outstanding coating ability**
- **Easy to remove**
- **Low viscosity**

Your first choice for cases where a highly dispersive and more liquid viscoelastic is needed at an attractive, efficient cost.

Specification	an-Viscose
Hydroxypropylmethylcellulose	2%
Viscosity* [mPas]	approx. 4,000 – 5,000
Osmolality [mOsm/kg]	270 - 400
Storage	2° - 25°C
pH	6.8 – 7.5
Contents [ml]	2.0 ml syringe
Shelf life [months]	60

*after steam sterilization